

PRECISION GROUND FLAT STOCK

MATERIAL:

BS 1407

C= 1.1
Si= 0.22
Mn= 0.37
Cr= 0.43
P= < 0.45
S= < 0.45

1.2210, 115 Cr V3

C=1. 10-1.25
Si= 0.15-0.30
Mn= 0.20-0.40
Cr= 0.50-0.80
V= 0.07-0.12
P= S=



LENGHT: 333 mm

Example of designation:
BSS 3 x 333

Silver steel
Ground bar
333 mm
BSS



Diameter	Description	Price VAT excl. Euro x100	% Price Change		Package
			1	2	
8,00	BSS 8 X 333	7,00	-	-	39

FEATURES

Supplied: annealed
Hardness HB 207-237
Tensile strenght 700 / 850 N/mm2

DIAMETER TOLERANCE

> 25 mm +0 / 0,015
< 25 mm +0 / 0,025

MATERIAL: BS 1407 o 1.2210, 115 Cr V3 according to stock availability

SURFACE FINISH

Roughness < 0,6 micron

THERMAL TREATMENT:

Hardening

In case of low carbon level, heat slowly up to 760-800 °C.

In case of high carbon level, maintain on minimum temperature. Leave the temperature uniforms. Then harden in well stirred (agited) water. Hardness reached after hardening: about 65-68 HRC. The approximate quench hardness is 65 to 68 Rc.

TEMPERING

Proceed with temperatures between 180 °C and 350 °C according to the usage needs and referring to the tempering curve (see below).

PACKAGING

Bars are protected from corrosion by applying a solution of lanolin.
In addition, all bars are carefully packed to prevent damage during handling and transport.

APPLICATIONS


Gauges, spindles, pins, various tools, punches, points, moulds accessories, e.t.c.

Technical informations are indicative and can be updated.

Copyright Gandini Fasteners S.r.l. All rights reserved. No part of this web site may be reproduced in any form without express permission.

GANDINI FASTENERS SRL viale Pier Paolo Pasolini, 83 - 20099 Sesto S.Giovanni Milano Italy

Tel. +39 02 241 047 250 Fax +39 02 241 047 74



Production and distribution
of fasteners, fixing elements
and mechanical parts
machining

GANDINI FASTENERS SRL
viale Pier Paolo Pasolini, 83
Sesto San Giovanni Mi - Italy

Sales department
250@gandini.it
tel +39 02 241 047 250

Administration
350@gandini.it
tel +39 02 241 047 350