

TECHNICAL PLASTIC AND METAL PARTS

									ver cap 06-k4
Code		Description	Price euro/1000	% Price (1	Change 2	Package	А	В	CDEFgr
006 5042 0	21 04	MP 06- 5- 4 CAPP.021	83,00	+ 60%	-	250	10.8	12.2	6

Colour	Colour numb								
beige 021 (XXX XXX XXX XXX XX)									
Colour descriptionbeigeMatchesCream.Featured colours reserved. Due to the		RAL colour 9001 and Trespa A05.1. in colour may occur.	.1						
Material		Material nr							
polyethylene Hd - PE		04 (XXX XXXX XXX XX)							
High pressure Polyethylene is resistar a little less than low pressure Polyethy insulating electrically. Polyethylene ca Features	lene, yet has a bett/	er scratch firmness. Does not take							
feature	DIN	Resistance to	Valutation						
Relative density gr/cm ³	0,95	Petrol	А						
Tensile strength MN/m ²	24 350 1000	Benzene	A						
Elongation at break %		Mineral oils	A A						
Tensile modulus MN/m ²		Vegetable oils							
Notched impact strength kJ/m ²	3	Weak alkalis	A						
Ball indentation MN/m ²	25	Strong alkalis	А						
Application temperature max °C	80	Weak acids	А						
Volume resistivity cm	10^15	Strong acids	В						
Dissapation factor tan. 10 ³ Hz	0,001	A = good							
Dielectric strength MV/m	53	53 B = doubtful							
Flammability UL94 > 1,6 mm	-	C = poor							
Coefficient of friction (on steel)	0,25-0,3								

Technical informations are indicative and can be updated.

Copyright Gandini Fasteners S.r.I. All rights reserved. No part of this web site may be reproduced in any form without express permission.

GANDINI FASTENERS SRL viale Pier Paolo Pasolini, 83 - 20099 Sesto S.Giovanni Milano Italy Tel. +39 02 241 047 250 Fax +39 02 241 047 74

Production and distribution of fasteners, fixing elements and mechanical parts machining

GANDINI FASTENERS SRL Sesto San Giovanni Mi - Italy **Sales department** 250@gandini.it tel +39 02 241 047 250

Administration 350@gandini.it tel +39 02 241 047 350