

TECHNICAL PLASTIC AND METAL PARTS

						0	ver cap 06-k4
Code	Description	Price euro/1000	% Price Change 1 2	e Package	A	В	CDEFgr
006 5042 022 04	MP 06- 5- 4 CAPP.022	83,00	+ 60% -	250	10.8	12.2	6

Colour	Colour numbe	er					
beige	022 (XXX XXXX XXX XX)						
Colour descriptionbeigeMatchesIvory. MatFeatured colours reserved. Due to the		es RAL colour 1014 and Trespa A in colour may occur.	.08.2.1				
Material		Material nr					
polyethylene Hd - PE		04 (XXX XXXX XXX XX)					
General informations: High pressure Polyethylene is resista a little less than low pressure Polyeth insulating electrically. Polyethylene ca	ylene, yet has a bette	er scratch firmness. Does not take ourns on after lighting it.					
Features		Chimical resistance					
feature	DIN	Resistance to	Valutation				
Relative density gr/cm ³	0,95	Petrol	А				
Tensile strength MN/m ²	24	Benzene	А				
Elongation at break %	350	Mineral oils	A				
Tensile modulus MN/m ²	1000	Vegetable oils	A				
Notched impact strength kJ/m ²	3	Weak alkalis	A				
Ball indentation MN/m ²	25	Strong alkalis	A				
Application temperature max °C	80	Weak acids	A				
Volume resistivity cm	10^15	Strong acids	В				
sapation factor tan. 10 ³ Hz 0,001		A = good					
Dielectric strength MV/m	53	B = doubtful					
Flammability UL94 > 1,6 mm	-	C = poor					
Coefficient of friction (on steel)	0,25-0,3						
All data are indicative							

Technical informations are indicative and can be updated.

Copyright Gandini Fasteners S.r.I. All rights reserved. No part of this web site may be reproduced in any form without express permission.

GANDINI FASTENERS SRL viale Pier Paolo Pasolini, 83 - 20099 Sesto S.Giovanni Milano Italy Tel. +39 02 241 047 250 Fax +39 02 241 047 74

Production and distribution of fasteners, fixing elements and mechanical parts machining

GANDINI FASTENERS SRL Sesto San Giovanni Mi - Italy **Sales department** 250@gandini.it tel +39 02 241 047 250

Administration 350@gandini.it tel +39 02 241 047 350