

TECHNICAL PLASTIC AND METAL PARTS

									Driv	/e fas 094	stene 1	r
Code	Description	Price euro/1000	% Price 0	Change	Package	٨	В	С	D	E		0
Coue	Description		1 1	2	Раскауе	A	D	-0	-0	L	F	Ϋ́
094 0260 699 01	MP 94-260 NERO	98,00	+ 60%	-	250	6.2	3.6	7.1	1.6	4.7	5.6	_

Colour	Colour num	ber				
ack 699 (XXX XXX XXX XXX)						
Colour descriptionblackMatchesbrillantFeatured colours reserved. Due to the		easonably matches RAL colour9005 is in colour may occur.	;			
Material		Material nr				
Nylon - 6 PA - 6 01 (XXX XXXX XXX XX)						
General informations: A strong, tough and durable material. Iubricant properties ideal for slide bea Always has to acclimatize for a few da	rings. Takes in app	rox 3% moisture at room temperatu	ire and is then at its strongest.			
Features		Chimical resistance				
feature	DIN	Resistance to	Valutation			
Relative density gr/cm ³	1,14	Petrol	А			
Tensile strength MN/m ²	55	Benzene	А			
Elongation at break %	250	Mineral oils	A			
Tensile modulus MN/m ²	950	Vegetable oils	А			
Notched impact strength kJ/m ²	35	Weak alkalis	A			
Ball indentation MN/m ²	82	Strong alkalis	В			
Application temperature max °C	120	Weak acids	В			
Volume resistivity cm	10^15	Strong acids	С			
Dissapation factor tan. 10 ³ Hz	0,2	A = good				
Dielectric strength MV/m	35	B = doubtful				
Flammability UL94 > 1,6 mm	V2	C = poor				
Coefficient of friction (on steel)	0,3					
All data are indicative						

Technical informations are indicative and can be updated.

Copyright Gandini Fasteners S.r.I. All rights reserved. No part of this web site may be reproduced in any form without express permission.

GANDINI FASTENERS SRL viale Pier Paolo Pasolini, 83 - 20099 Sesto S.Giovanni Milano Italy Tel. +39 02 241 047 250 Fax +39 02 241 047 74

Production and distribution of fasteners, fixing elements and mechanical parts machining

GANDINI FASTENERS SRL Sesto San Giovanni Mi - Italy **Sales department** 250@gandini.it tel +39 02 241 047 250

Administration 350@gandini.it tel +39 02 241 047 350