

TECHNICAL PLASTIC AND METAL PARTS

										r off ca 040	đ
Code	Description	Price euro/1000	% Price (1	Change 2	Package	А	В	С	D	E	Fgr
040 0213 000 03	MP 40-213	165,00	+ 60%	-	250	21.5	23.2	14.9	13.5	19.5	

Colour	Colour numbe	r						
transparent - natural	000 (XXX XX	000 (XXX XXXX XXX XX)						
Colour descriptiontransparent -MatchesNatural matoFeatured colours reserved. Due to the	hes Milk-like; transpa	rrent white colour can differ per kir in colour may occur.	nd of material.					
Material		Material nr						
polyethylene Ld - PE		03 (XXX XXXX XXX XX)						
General informations: Low pressure polyethylene is resistar great flexibilty it is almost unbreakabl can not be glued and burns on after li	e. Does not take in m							
Features		Chimical resistance						
feature	DIN	Resistance to	Valutation					
Relative density gr/cm ³	0,92	Petrol	А					
Tensile strength MN/m ²	10	Benzene	А					
Elongation at break %	300	Mineral oils	А					
Tensile modulus MN/m ²	180	Vegetable oils	A					
Notched impact strength kJ/m ²	-	Weak alkalis	А					
Ball indentation MN/m ²	14	Strong alkalis	А					
Application temperature max °C	70	Weak acids	А					
Volume resistivity cm	10^17	Strong acids	В					
Dissapation factor tan. 10 ³ Hz	0,0003	A = good						
Dielectric strength MV/m	60	B = doubtful						
Flammability UL94 > 1,6 mm	-	C = poor						
Coefficient of friction (on steel)	0,17-1,5							
All data are indicative								

Technical informations are indicative and can be updated.

Copyright Gandini Fasteners S.r.I. All rights reserved. No part of this web site may be reproduced in any form without express permission.

GANDINI FASTENERS SRL viale Pier Paolo Pasolini, 83 - 20099 Sesto S.Giovanni Milano Italy Tel. +39 02 241 047 250 Fax +39 02 241 047 74

Production and distribution of fasteners, fixing elements and mechanical parts machining

GANDINI FASTENERS SRL Sesto San Giovanni Mi - Italy **Sales department** 250@gandini.it tel +39 02 241 047 250

Administration 350@gandini.it tel +39 02 241 047 350