


TECHNICAL PLASTIC AND METAL PARTS



Code	Description	Price euro/1000	% Price Change 1 2	Package	А	В	CDEFgr
200 3625 073 02	MP 200 - 3625 GIALLO	100,00	+ 60% -	100	3,6	250	74

olour Colour number								
Yellow	073 (XXX XXXX XXX XX)							
Colour description Matches		Yellow						
Featured colours reserved. Due to the	e screen, difference	es in colour may occur.						
Material		Material nr						
Nylon - 66 PA - 66		02 (XXX XXXX XXX XX)						
General informations: A strong, tough and durable material. selflubricant properties ideal for slide strongst. Therefore always has to acc Nylon is self extinguishing.	bearings. Takes in	approx 2 % moisture (a little less that	an nylon-6) and is then at its					
Features		Chimical resistance						
feature	DIN	Resistance to	Valutation					
Relative density gr/cm ³	1,14	Petrol	А					
Tensile strength MN/m ²	60	Benzene	А					
Elongation at break %	140	Mineral oils	Α					
Tensile modulus MN/m ²	1500	Vegetable oils	Α					
Notched impact strength kJ/m ²	17	Weak alkalis	А					
Ball indentation MN/m ²	100	Strong alkalis	В					
	100 120	Strong alkalis Weak acids	B B					
Application temperature max °C		0	_					
Application temperature max °C Volume resistivity cm	120	Weak acids Strong acids	В					
Application temperature max °C Volume resistivity cm Dissapation factor tan. 10 ³ Hz	120 10^15	Weak acids Strong acids A = good B = doubtful	В					
Application temperature max °C Volume resistivity cm Dissapation factor tan. 10 ³ Hz Dielectric strength MV/m	120 10^15 0,15	Weak acids Strong acids A = good	В					
Ball indentation MN/m ² Application temperature max °C Volume resistivity cm Dissapation factor tan. 10 ³ Hz Dielectric strength MV/m Flammability UL94 > 1,6 mm Coefficient of friction (on steel)	120 10^15 0,15 30	Weak acids Strong acids A = good B = doubtful	В					

Technical informations are indicative and can be updated.

Copyright Gandini Fasteners S.r.I. All rights reserved. No part of this web site may be reproduced in any form without express permission.

GANDINI FASTENERS SRL viale Pier Paolo Pasolini, 83 - 20099 Sesto S.Giovanni Milano Italy Tel. +39 02 241 047 250 Fax +39 02 241 047 74

Production and distribution of fasteners, fixing elements and mechanical parts machining

GANDINI FASTENERS SRL Sesto San Giovanni Mi - Italy **Sales department** 250@gandini.it tel +39 02 241 047 250

Administration 350@gandini.it tel +39 02 241 047 350