

PRECISION GROUND FLAT STOCK

MATERIAL: BS 1407 C= 1.1 Si= 0.22 Mn= 0.37 Cr= 0.43 P= < 0.45 S= < 0.45

1.2210, 115 Cr V3

C=1.10 ÷1.25 Si= 0.15 ÷ 0.30 Mn= 0.20 ÷ 0.40 Cr= 0.50 ÷ 0.80 V= 0.07 ÷ 0.12

V= 0.07 ÷ 0.12 P= < 0.03 S= < 0.03



LENGHT: 1000 mm

Example of designation:

CSS 3 x 1000



Diameter	Description	Price VAT excl. Euro x100	% Price 1	Change 2	Package
4,00	CSS 4 X 1000	7,00	-	-	1

FEATURES

Supplied: annealed Hardeness HB 207-237 Tensile strenght 700 / 850 N/mm2

DIAMETER TOLERANCE

> 25 mm +0 / 0,015 < 25 mm +0 / 0,025

MATERIAL: BS 1407 o 1.2210, 115 Cr V3 according to stock availability

SURFACE FINISH

Roughness < 0,6 micron

THERMAL TREATMENT:

Hardening

In case of low carbon level, heat slowly up to 760-800 °C.

In case of high carbon level, maintain on minimum temperature. Leave the temperature uniforms. Then harden in well stirred (agited) water. Hardness reached after hardening: about 65-68 hrc. The approximate quench hardness is 65 to 68 Rc.

TEMPERING

Proceed with temperatures between 180 °C and 350 °C according to the usage needs and referring to the tempering curve (see below).

PACKAGING

Bars are protected from corrosion by applying a solution of lanolin.

In addition, all bars are carefully packed to prevent damage during handling and transport.


APPLICATIONS

Gauges, spindles, pins, various tools, punches, points, moulds accessories, e.t.c.

Technical informations are indicative and can be updated.

Copyright Gandini Fasteners S.r.l. All rights reserved. No part of this web site may be reproduced in any form without express permission.

GANDINI FASTENERS SRL viale Pier Paolo Pasolini, 83 - 20099 Sesto S.Giovanni Milano Italy Tel. +39 02 241 047 250 Fax +39 02 241 047 74



Production and distribution of fasteners, fixing elements and mechanical parts
machining

GANDINI PASTENERS SRE viale Pier Paolo Pasolini, 83
Sesto San Giovanni Mi - Italy

GANDINI FASTENERS SRL Sesto San Giovanni Mi - Italy **Sales department** 250@gandini.it tel +39 02 241 047 250

Administration 350@gandini.it tel +39 02 241 047 350