


PRECISION GROUND FLAT STOCK




Width L	Thickness s	Description	Price VAT excl. Euro x100	% Price 1	Change 2	Package
20,00	1,50	GFS 20 X 1,5 X 1000 - 01	40,00	-	-	1

FEATURES

Supplyed annealed Free of decarburization Max. Hardness 63 HRC

AVAILABLE DIMENSIONS

Lenght 1000 mm section: see dimension table Thickness tolerance + 0,05 / -0,00Width tolerance + 0,2 / -0,0Lenght tolerance + 5 / -0



MATERIAL: AISI 01 - Cold work tool steel

AISI 01, 1.2510 Tool steel for generic use, hardenable in oil, not subject to deformations. Thermal treatment on this kind of tool steel for cold processes is less complicated than others at higher alloy.

THERMAL TREATMENTS:

Hardening in oil

Preheat at 300/500 °C before reaching hardness temperature of 780/820 °C

Tempering

Proceed with temperatures between 150 °C and 350 °C according to the usage needs and referring to the tempering curve. Ex. 1 hour at 150° = hardness HRC 63-64

- Ex. 1 hour at 200° = hardness HRC 61-62
- Ex. 1 hour at 250° = hardness HRC 58-60
- Ex. 1 hour at 300° = hardness HRC 54-56

PACKAGING

Single package in order to protect bar during handling and transport

APPLICATIONS

Dies medium passage, tools for particular presses, punches for drawing, pins, bushes, bits for lathe, lathe jaws, engraving cutters, blades for tear-off machines, calibrated caps, threaded gauges and precision tools as cams, blade to cut the fabric, reamers, collets, knife cutters, cut strips, trimmers, expander rollers, plastic moulds, accessories for moulds and knives for wood processing.

Technical informations are indicative and can be updated.

Copyright Gandini Fasteners S.r.I. All rights reserved. No part of this web site may be reproduced in any form without express permission.

GANDINI FASTENERS SRL viale Pier Paolo Pasolini, 83 - 20099 Sesto S.Giovanni Milano Italy Tel. +39 02 241 047 250 Fax +39 02 241 047 74

Production and distribution of fasteners, fixing elements and mechanical parts machining

GANDINI FASTENERS SRL Sesto San Giovanni Mi - Italy **Sales department** 250@gandini.it tel +39 02 241 047 250

Administration 350@gandini.it tel +39 02 241 047 350