

PRECISION GROUND FLAT STOCK

MATERIAL:

AISI 01, 1.2510

Tool steel for cold processes

C= 0.95

Si= 0.20

Mn= 1.20

Cr= 0.60

W= 0.60

V= 0.10

Example of designation:

GFS 25 x 8 x 500 - 01



s= thickness
L= width

LENGHT: 500 mm

Ground flat stock
500 mm
GFS-01



Width L	Thickness s	Description	Price VAT excl. Euro x100	% Price Change 1	% Price Change 2	Package
10,00	2,00	GFS 10 X 2 X 500 - 01	19,00	-	-	1

SUPPLIED

Supplied annealed

Free of decarburization

Maximum hardness obtainable 63 HRC

AVAILABLE DIMENSIONS

Lenght 500 mm

Section: see dimension table

Thickness tolerance

+ 0,05 / -0,00

Width tolerance

+ 0,2 / -0,0

Lenght tolerance

+ 5 / -0



MATERIAL: AISI 01, 1.2510

Tool steel for generic use, hardenable in oil, not subject to deformations.

Thermal treatment on this kind of tool steel for cold processes is less complicated than others at higher alloy.

THERMAL TREATMENT:

Hardening in oil

Preheat up to 300/500 °C before reaching hardness temperature of 780/820 °C.

Tempering

proceed with temperatures between 150 °C and 350 °C according to the usage needs and referring to the tempering curve.

Ex. 1 hour at 150° = hardness HRC 63-64

Ex. 1 hour at 200° = hardness HRC 61-62

Ex. 1 hour at 250° = hardness HRC 58-60

Ex. 1 hour at 300° = hardness HRC 54-56

PACKAGING

Bars are always supplied oiled and individually packaged to avoid and prevent damage during handling and transport.

APPLICATIONS

Dies medium passage, tools for particular presses, punches for drawing, pins, bushes, bits for lathe, lathe jaws, engraving cutters, blades for tear-off machines, calibrated caps, threaded gauges and precision tools as cams, blade to cut the fabric, reamers, collets, knife cutters, cut strips, trimmers, expander rollers, plastic moulds, accessories for moulds and knives for wood processing.

Technical informations are indicative and can be updated.

Copyright Gandini Fasteners S.r.l. All rights reserved. No part of this web site may be reproduced in any form without express permission.

GANDINI FASTENERS SRL viale Pier Paolo Pasolini, 83 - 20099 Sesto S. Giovanni Milano Italy

Tel. +39 02 241 047 250 Fax +39 02 241 047 74

Production and distribution
of fasteners, fixing elements
and mechanical parts
machining

GANDINI FASTENERS SRL
viale Pier Paolo Pasolini, 83
Sesto San Giovanni Mi - Italy

Sales department
250@gandini.it
tel +39 02 241 047 250

Administration
350@gandini.it
tel +39 02 241 047 350