

TECHNICAL PLASTIC AND METAL PARTS

Drive fastener 137

Code	Description	Price euro/1000	% Price (Change 2	Package	Α	В	C D	Е	F gr
137 0050 000 05	MP 137-05	174,00	+ 60%	-	500	7.8	1.5	7 14	2.4	19

transparent - natural

Colour description
Matches
Natural matches Milk-like; transparent white colour can differ per kind of material.
Featured colours reserved. Due to the screen, differences in colour may occur.

MaterialMaterial nrPolyoxymethylene (POM) POM05 (XXX XXXX XXX)

General informations:

Strong durable material, suitable for flexible connection elements and numerous other technical products. Resembles nylon, yet the taking in of moisture is less than 0,5%, so a higher dimensional stability is reached and is very well insulating electrically. Suitable for suspending clamps, bearings, gear-wheels etc. POM can be glued.

Features		Chimical resistance			
feature	DIN	Resistance to	Valutation A		
Relative density gr/cm ³	1,42	Petrol			
Tensile strength MN/m ²	75	Benzene	Α		
Elongation at break %	65	Mineral oils	Α		
Tensile modulus MN/m ²	3000	Vegetable oils	Α		
Notched impact strength kJ/m ²	8.5	Weak alkalis	Α		
Ball indentation MN/m ²	140	Strong alkalis	В		
Application temperature max °C	100	Weak acids	-		
Volume resistivity cm	10^15	Strong acids	С		
Dissapation factor tan. 10 ³ Hz	0,025	A = good			
Dielectric strength MV/m	70	B = doubtful			
Flammability UL94 > 1,6 mm	HB	C = poor			
Coefficient of friction (on steel)	0,25				
All data are indicative					

Technical informations are indicative and can be updated.

Copyright Gandini Fasteners S.r.I. All rights reserved. No part of this web site may be reproduced in any form without express permission.

GANDINI FASTENERS SRL viale Pier Paolo Pasolini, 83 - 20099 Sesto S.Giovanni Milano Italy Tel. +39 02 241 047 250 Fax +39 02 241 047 74

Production and distribution of fasteners, fixing elements and mechanical parts
machining

GANDINI PASTENERS SRE viale Pier Paolo Pasolini, 83
Sesto San Giovanni Mi - Italy

GANDINI FASTENERS SRL Sesto San Giovanni Mi - Italy **Sales department** 250@gandini.it tel +39 02 241 047 250

Administration 350@gandini.it tel +39 02 241 047 350