

TECHNICAL PLASTIC AND METAL PARTS

						G	ear w 10	/heel 4	
Code	Description	Price euro/1000	% Price Change	Package					gr
104 0016 000 05	MP 104-16	14.051,00	+ 60% -	1	2 15	3 18	15	25	

Colour	Colour number	r				
transparent - natural	000 (XXX XXXX XXX XX)					
Colour descriptiontransparentMatchesNatural maFeatured colours reserved. Due to t	tches Milk-like; transpa	rent white colour can differ per kind n colour may occur.	d of material.			
Material		Material nr				
Polyoxymethylene (POM) POM		05 (XXX XXXX XXX XX)				
General informations: Strong durable material, suitable for yet the taking in of moisture is less t electrically. Suitable for suspending	han 0,5%, so a higher of	dimensional stability is reached and				
Features		Chimical resistance				
feature	DIN	Resistance to	Valutation			
Relative density gr/cm ³	1,42	Petrol	А			
Tensile strength MN/m ²	75	Benzene	А			
Elongation at break %	65	Mineral oils	А			
Tensile modulus MN/m ²	3000	Vegetable oils	А			
Notched impact strength kJ/m ²	8.5	Weak alkalis	А			
Ball indentation MN/m ²	140	Strong alkalis	В			
Application temperature max °C	100	Weak acids	-			
Volume resistivity cm	10^15	Strong acids	С			
Dissapation factor tan. 10 ³ Hz	0,025	A = good				
Dielectric strength MV/m	70	B = doubtful				
Flammability UL94 > 1,6 mm	HB	C = poor				
Coefficient of friction (on steel)	0,25					
All data are indicative						

Technical informations are indicative and can be updated.

Copyright Gandini Fasteners S.r.I. All rights reserved. No part of this web site may be reproduced in any form without express permission.

GANDINI FASTENERS SRL viale Pier Paolo Pasolini, 83 - 20099 Sesto S.Giovanni Milano Italy Tel. +39 02 241 047 250 Fax +39 02 241 047 74

Production and distribution of fasteners, fixing elements and mechanical parts machining

GANDINI FASTENERS SRL Sesto San Giovanni Mi - Italy **Sales department** 250@gandini.it tel +39 02 241 047 250

Administration 350@gandini.it tel +39 02 241 047 350