

TECHNICAL PLASTIC AND METAL PARTS

Torx caps 158

I	Code	Description	Price euro/1000	% Price C	Change	Package	Α	В	С	D	Е	F gr
				1	2							
	158 0130 318 03	MP 158-1-30 GRIGIO	76,00	+ 60%	-	500	40	18	15.2	0.1	2.4	F2

Colour	Colour number				
grey	318 (XXX XXXX XXX XX)				
Colour description	grey				
Matches					
Featured colours reserved. Due to the screen, differences in colour may occur.					

Material		Material nr				
polyethylene Ld - PE		03 (XXX XXXX XXX XX)				
General informations: Low pressure polyethylene is resistan great flexibilty it is almost unbreakable can not be glued and burns on after lig	e. Does not take in m					
Features		Chimical resistance				
feature	DIN	Resistance to	Valutation			
Relative density gr/cm ³	0,92	Petrol	Α			
Tensile strength MN/m ²	10	Benzene	Α			
Elongation at break %	300	Mineral oils	Α			
Tensile modulus MN/m ²	180	Vegetable oils	Α			
Notched impact strength kJ/m ²	-	Weak alkalis	Α			
Ball indentation MN/m ²	14	Strong alkalis	Α			
Application temperature max °C	70	Weak acids	Α			
Volume resistivity cm	10^17	Strong acids	В			
Dissapation factor tan. 10 ³ Hz	0,0003	A = good				
Dielectric strength MV/m	60	B = doubtful				
Flammability UL94 > 1,6 mm	-	C = poor				
Coefficient of friction (on steel)	0,17-1,5					
All data are indicative						

Technical informations are indicative and can be updated.

Copyright Gandini Fasteners S.r.l. All rights reserved. No part of this web site may be reproduced in any form without express permission.

GANDINI FASTENERS SRL viale Pier Paolo Pasolini, 83 - 20099 Sesto S.Giovanni Milano Italy Tel. +39 02 241 047 250 Fax +39 02 241 047 74

Production and distribution of fasteners, fixing elements and mechanical parts
machining

GANDINI PASTENERS SRE viale Pier Paolo Pasolini, 83
Sesto San Giovanni Mi - Italy

GANDINI FASTENERS SRL Sesto San Giovanni Mi - Italy **Sales department** 250@gandini.it tel +39 02 241 047 250

Administration 350@gandini.it tel +39 02 241 047 350