

TECHNICAL PLASTIC AND METAL PARTS

								Prot	ectior 061	ı plug
Code	Description	Price euro/1000	% Price Ch		Package	A	В	С	D	E F gr
061 0091 000 03	MP 61-0091	68,00	+ 60%	2 -	1000	9.1	7.9	12.9	6.4	

Colour	Colour numbe	r						
transparent - natural	000 (XXX XXXX XXX XX)							
Colour descriptiontransparenMatchesNatural maFeatured colours reserved. Due to the	tches Milk-like; transpa	rent white colour can differ per kir in colour may occur.	nd of material.					
Material		Material nr						
polyethylene Ld - PE		03 (XXX XXXX XXX XX)						
General informations: Low pressure polyethylene is resist great flexibilty it is almost unbreaka can not be glued and burns on after	ble. Does not take in m							
Features		Chimical resistance						
feature	DIN	Resistance to	Valutation					
Relative density gr/cm ³	0,92	Petrol	А					
Tensile strength MN/m ²	10	Benzene	А					
Elongation at break %	300	Mineral oils	A					
Tensile modulus MN/m ²	180	Vegetable oils	А					
Notched impact strength kJ/m ²	-	Weak alkalis	А					
Ball indentation MN/m ²	14	Strong alkalis	А					
Application temperature max °C	70	Weak acids	А					
Volume resistivity cm	10^17	Strong acids	В					
Dissapation factor tan. 10 ³ Hz	0,0003	A = good						
Dielectric strength MV/m 60		B = doubtful						
Flammability UL94 > 1,6 mm	-	C = poor						
Coefficient of friction (on steel)	0,17-1,5							
All data are indicative								

Technical informations are indicative and can be updated.

Copyright Gandini Fasteners S.r.I. All rights reserved. No part of this web site may be reproduced in any form without express permission.

GANDINI FASTENERS SRL viale Pier Paolo Pasolini, 83 - 20099 Sesto S.Giovanni Milano Italy Tel. +39 02 241 047 250 Fax +39 02 241 047 74

Production and distribution of fasteners, fixing elements and mechanical parts machining

GANDINI FASTENERS SRL Sesto San Giovanni Mi - Italy **Sales department** 250@gandini.it tel +39 02 241 047 250

Administration 350@gandini.it tel +39 02 241 047 350