

TECHNICAL PLASTIC AND METAL PARTS

										w DIN 4017
Code	Description	Price euro/1000	% Price (1	Change 2	Package			С		E F gr
079 0880 000 02	MP 79- 8-80	539,00	+ 60%	-	50	M8	80	5.5	13	

Colour	plour Colour number									
transparent - natural 000 (XXX XXX XXX XXX XX)										
Colour descriptiontransparent -MatchesNatural matoFeatured colours reserved. Due to the	hes Milk-like; trans	parent white colour can differ per ki s in colour may occur.	nd of material.							
Material		Material nr								
Nylon - 66 PA - 66		02 (XXX XXXX XXX XX)								
General informations: A strong, tough and durable material. selflubricant properties ideal for slide strongst. Therefore always has to acc Nylon is self extinguishing.	bearings. Takes in	approx 2 % moisture (a little less th	an nylon-6) and is then at its							
Features		Chimical resistance								
feature	DIN	Resistance to	Valutation							
Relative density gr/cm ³	1,14	Petrol	А							
Tensile strength MN/m ²	60	Benzene	А							
Elongation at break %	140	Mineral oils	А							
Tensile modulus MN/m ²	1500	Vegetable oils	A							
Notched impact strength kJ/m ²	17	Weak alkalis	A							
Ball indentation MN/m ²	100	Strong alkalis	В							
Application temperature max °C	120	Weak acids	В							
Volume resistivity cm	10^15	Strong acids	С							
Dissapation factor tan. 10 ³ Hz	0,15	A = good								
Dielectric strength MV/m	30	B = doubtful								
Flammability UL94 > 1,6 mm	V2	C = poor								
Coefficient of friction (on steel)	0,3									
All data are indicative										

Technical informations are indicative and can be updated. Copyright Gandini Fasteners S.r.I. All rights reserved. No part of this web site may be reproduced in any form without express permission.

GANDINI FASTENERS SRL viale Pier Paolo Pasolini, 83 - 20099 Sesto S.Giovanni Milano Italy Tel. +39 02 241 047 250 Fax +39 02 241 047 74

Production and distribution of fasteners, fixing elements and mechanical parts machining

GANDINI FASTENERS SRL Sesto San Giovanni Mi - Italy **Sales department** 250@gandini.it tel +39 02 241 047 250

Administration 350@gandini.it tel +39 02 241 047 350