

TECHNICAL PLASTIC AND METAL PARTS

Photo clip
046

Code	Description	Price euro/1000	% Price Change	Package	A	B	C	D	E	F	gr
			1 2								
046 1080 225 11	MP 46- 1- 8 GRIGIO	266,00	+ 60%	-	100	7.8	8	16	3.5	25	F2

Colour	Colour number
	(XXX XXXX XXX XX)
Colour description Matches Featured colours reserved. Due to the screen, differences in colour may occur.	

Material		Material nr	
polypropylene PP		11 (XXX XXXX XXX XX)	
General informations: Relatively strong material which does not take in moisture and is very well resistant to scratching. Warmth resistant up to 120°C. Therefore suitable for technical as well as domestic products, such as caps, hinges, kitchen utensils. Owing to good insulating properties, often applied to electro-industry.			
Features		Chemical resistance	
feature	DIN	Resistance to	Valutation
Relative density gr/cm ³	1,57	Petrol	B
Tensile strength MN/m ²	32	Benzene	C
Elongation at break %	350	Mineral oils	B
Tensile modulus MN/m ²	1300	Vegetable oils	A
Notched impact strength kJ/m ²	6.5	Weak alkalis	A
Ball indentation MN/m ²	65	Strong alkalis	A
Application temperature max °C	110	Weak acids	A
Volume resistivity cm	10^16	Strong acids	B
Dissapation factor tan. 10 ³ Hz	0,0005	A = good B = doubtful C = poor	
Dielectric strength MV/m	80		
Flammability UL94 > 1,6 mm	HB		
Coefficient of friction (on steel)	0,5		
All data are indicative			

Technical informations are indicative and can be updated.

Copyright Gandini Fasteners S.r.l. All rights reserved. No part of this web site may be reproduced in any form without express permission.

GANDINI FASTENERS SRL viale Pier Paolo Pasolini, 83 - 20099 Sesto S.Giovanni Milano Italy
Tel. +39 02 241 047 250 Fax +39 02 241 047 74

Production and distribution
of fasteners, fixing elements
and mechanical parts
machining

GANDINI FASTENERS SRL
viale Pier Paolo Pasolini, 83
Sesto San Giovanni Mi - Italy

Sales department
250@gandini.it
tel +39 02 241 047 250

Administration
350@gandini.it
tel +39 02 241 047 350