

046 1030 225 11

2.9 3 16 3.5 25 F2

TECHNICAL PLASTIC AND METAL PARTS

MP 46- 1- 3 GRIGIO

						Photo cl 046	ip
Code	Description	Price euro/1000	% Price Change	Package A	ВС	D E	F gr

+ 60%

-

100

211,00

Colour	Colour numb (XXX XXX	oer X XXX XX)	
Colour description Matches Featured colours reserved. Due to the	e screen, difference	s in colour may occur.	
Material		Material nr	
polypropylene PP		11 (XXX XXXX XXX XX)	
Relatively strong material which does 120°C. Therefore suitable for technica insulating properties, often applied to Features	al as well as domes		
feature	DIN	Resistance to	Valutation
Relative density gr/cm ³	1,57	Petrol	В
Tensile strength MN/m ²	32	Benzene	С
Elongation at break %	350	Mineral oils	В
Tensile modulus MN/m ²	1300	Vegetable oils	А
Notched impact strength kJ/m ²	6.5	Weak alkalis	А
Ball indentation MN/m ²	65	Strong alkalis	А
Application temperature max °C	110	Weak acids	А
/olume resistivity cm	10^16	Strong acids	В
Dissapation factor tan. 10 ³ Hz	0,0005	A = good	
Dielectric strength MV/m	80	B = doubtful	
Flammability UL94 > 1,6 mm	HB	C = poor	
Coefficient of friction (on steel)	0,5		
All data are indicative			

Technical informations are indicative and can be updated.

Copyright Gandini Fasteners S.r.I. All rights reserved. No part of this web site may be reproduced in any form without express permission.

GANDINI FASTENERS SRL viale Pier Paolo Pasolini, 83 - 20099 Sesto S.Giovanni Milano Italy Tel. +39 02 241 047 250 Fax +39 02 241 047 74

Production and distribution of fasteners, fixing elements and mechanical parts machining

GANDINI FASTENERS SRL Sesto San Giovanni Mi - Italy **Sales department** 250@gandini.it tel +39 02 241 047 250

Administration 350@gandini.it tel +39 02 241 047 350