

**TECHNICAL PLASTIC AND METAL PARTS** 

								Ph	oto ( 046		
	Code	Description	Price euro/1000	% Price Char 1 2		A	ВC	D	Ε	Fg	jr
04	46 1030 113 11	MP 46- 1- 3 BIANCO	211,00	+ 60% -	· 100	2.9	3 16	3.5	25	F2	

Colour	Colour numb	per				
white	113 (XXX)	(XXX <b>XXX</b> XX)				
Colour descriptionwhMatcheswhFeatured colours reserved. Due to the	ite. Matches: Roug	hly matches RAL colour 9003 s in colour may occur.				
Material		Material nr				
polypropylene PP		11 (XXX XXXX XXX <b>XX</b> )				
<b>General informations:</b> Relatively strong material which does 120°C. Therefore suitable for technica insulating properties, often applied to	al as well as domes	tic products, such as caps, hinges,				
Features		Chimical resistance				
feature	DIN	Resistance to	Valutation			
Relative density gr/cm <sup>3</sup>	1,57	Petrol	В			
Tensile strength MN/m <sup>2</sup>	32	Benzene	С			
Elongation at break %	350	Mineral oils	В			
Tensile modulus MN/m <sup>2</sup>	1300	Vegetable oils	A			
Notched impact strength kJ/m <sup>2</sup>	6.5	Weak alkalis	A			
Ball indentation MN/m <sup>2</sup>	65	Strong alkalis	А			
Application temperature max °C	110	Weak acids	А			
Volume resistivity cm	10^16	Strong acids	В			
Dissapation factor tan. 10 <sup>3</sup> Hz	0,0005	A = good				
Dielectric strength MV/m	80	B = doubtful				
Flammability UL94 > 1,6 mm	HB	<b>C</b> = poor				
Coefficient of friction (on steel)	0,5					
All data are indicative						

Technical informations are indicative and can be updated.

Copyright Gandini Fasteners S.r.I. All rights reserved. No part of this web site may be reproduced in any form without express permission.

GANDINI FASTENERS SRL viale Pier Paolo Pasolini, 83 - 20099 Sesto S.Giovanni Milano Italy Tel. +39 02 241 047 250 Fax +39 02 241 047 74

Production and distribution of fasteners, fixing elements and mechanical parts machining

**GANDINI FASTENERS SRL** Sesto San Giovanni Mi - Italy **Sales department** 250@gandini.it tel +39 02 241 047 250

Administration 350@gandini.it tel +39 02 241 047 350