

TECHNICAL PLASTIC AND METAL PARTS

Paperclip
044

Code	Description	Price euro/1000	% Price Change	Package	A	B	C	DE	F	gr
044 0003 351 01	MP 44 -3 GIALLO FOSFORESCENTE	618,00	+ 60%	-	50	52	32	25	F1	

Colour	Colour number
transparent yellow	351 (XXX XXXX XXX XX)
Colour description	transparent yellow
Matches	yellow
Featured colours reserved. Due to the screen, differences in colour may occur.	

Material		Material nr	
Nylon - 6 PA - 6		01 (XXX XXXX XXX XX)	
General informations: A strong, tough and durable material. Suitable for connecting elements and other technical components. Owing to self lubricant properties ideal for slide bearings. Takes in approx 3% moisture at room temperature and is then at its strongest. Always has to acclimatize for a few days. Operational temperature up to approx 120°C. Nylon is self extinguishing.			
Features		Chemical resistance	
feature	DIN	Resistance to	Valutation
Relative density gr/cm ³	1,14	Petrol	A
Tensile strength MN/m ²	55	Benzene	A
Elongation at break %	250	Mineral oils	A
Tensile modulus MN/m ²	950	Vegetable oils	A
Notched impact strength kJ/m ²	35	Weak alkalis	A
Ball indentation MN/m ²	82	Strong alkalis	B
Application temperature max °C	120	Weak acids	B
Volume resistivity cm	10^15	Strong acids	C
Dissapation factor tan. 10 ³ Hz	0,2	A = good B = doubtful C = poor	
Dielectric strength MV/m	35		
Flammability UL94 > 1,6 mm	V2		
Coefficient of friction (on steel)	0,3		
All data are indicative			

Technical informations are indicative and can be updated.

Copyright Gandini Fasteners S.r.l. All rights reserved. No part of this web site may be reproduced in any form without express permission.

GANDINI FASTENERS SRL viale Pier Paolo Pasolini, 83 - 20099 Sesto S.Giovanni Milano Italy
Tel. +39 02 241 047 250 Fax +39 02 241 047 74

Production and distribution
of fasteners, fixing elements
and mechanical parts
machining

GANDINI FASTENERS SRL
viale Pier Paolo Pasolini, 83
Sesto San Giovanni Mi - Italy

Sales department
250@gandini.it
tel +39 02 241 047 250

Administration
350@gandini.it
tel +39 02 241 047 350