

## TECHNICAL PLASTIC AND METAL PARTS

Clip label 028

| Code            | Description     | Price euro/1000 | % Price Ch<br>1 | nange<br>2 | Package | Α  | В  | CDEFgr |
|-----------------|-----------------|-----------------|-----------------|------------|---------|----|----|--------|
| 028 0002 113 11 | MP 28- 2 BIANCO | 112,00          | + 60%           | -          | 250     | 70 | 20 | 6      |

Colour Colour number

white 113 (XXX XXXX XXX XXX)

Colour description white Matches white. Matches: Roughly matches RAL colour 9003
Featured colours reserved. Due to the screen, differences in colour may occur.

MaterialMaterial nrpolypropylene PP11 (XXX XXXX XXX)

## **General informations:**

Relatively strong material which does not take in moisture and is very well resistant to scratching. Warmth resistant up to 120°C. Therefore suitable for technical as well as domestic products, such as caps, hinges, kitchen utensils. Owing to good insulating properties, often applied to electro-industry.

| Features                                   |        | Chimical resistance |            |  |  |  |
|--|--------|---------------------|------------|--|--|--|
| feature                                    | DIN    | Resistance to       | Valutation |  |  |  |
| Relative density gr/cm <sup>3</sup>        | 1,57   | Petrol              | В          |  |  |  |
| Tensile strength MN/m <sup>2</sup>         | 32     | Benzene             | С          |  |  |  |
| Elongation at break %                      | 350    | Mineral oils        | В          |  |  |  |
| Tensile modulus MN/m <sup>2</sup>          | 1300   | Vegetable oils      | Α          |  |  |  |
| Notched impact strength kJ/m <sup>2</sup>  | 6.5    | Weak alkalis        | Α          |  |  |  |
| Ball indentation MN/m <sup>2</sup>         | 65     | Strong alkalis      | Α          |  |  |  |
| Application temperature max °C             | 110    | Weak acids          | Α          |  |  |  |
| Volume resistivity cm                      | 10^16  | Strong acids        | В          |  |  |  |
| Dissapation factor tan. 10 <sup>3</sup> Hz | 0,0005 | A = good            |            |  |  |  |
| Dielectric strength MV/m                   | 80     | <b>B</b> = doubtful |            |  |  |  |
| Flammability UL94 > 1,6 mm                 | HB     | C = poor            |            |  |  |  |
| Coefficient of friction (on steel)         | 0,5    |                     |            |  |  |  |
| All data are indicative                    |        |                     |            |  |  |  |

Technical informations are indicative and can be updated.

Copyright Gandini Fasteners S.r.l. All rights reserved. No part of this web site may be reproduced in any form without express permission.

**GANDINI FASTENERS SRL** viale Pier Paolo Pasolini, 83 - 20099 Sesto S.Giovanni Milano Italy Tel. +39 02 241 047 250 Fax +39 02 241 047 74

Production and distribution of fasteners, fixing elements and mechanical parts
machining

GANDINI PASTENERS SRE viale Pier Paolo Pasolini, 83
Sesto San Giovanni Mi - Italy

**GANDINI FASTENERS SRL** Sesto San Giovanni Mi - Italy **Sales department** 250@gandini.it tel +39 02 241 047 250

Administration 350@gandini.it tel +39 02 241 047 350