

TECHNICAL PLASTIC AND METAL PARTS

Roundbelt
022

| Code | Description | Price euro/1000 | % Price Change | Package | A | B | C | D | E | F | gr |
|-----------------|----------------|-----------------|----------------|---------|----|----|-----|----|----|----|----|
| | | | 1 2 | | | | | | | | |
| 022 0150 673 20 | MP 22-15 VERDE | 41.977,00 | + 60% | - | 25 | 15 | 120 | 23 | 27 | 12 | 8 |

| Colour | Colour number |
|--|---|
| green | 673 (XXX XXXX XXX XX) |
| Colour description | green |
| Matches | green. Matches: Matches RAL colour 6000 |
| Featured colours reserved. Due to the screen, differences in colour may occur. | |

| Material | | Material nr | |
|--|------------|----------------------------|------------|
| polyurethane PUR | | 20 (XXX XXXX XXX XX) | |
| General informations: | | | |
| A flexible plastic which lasts. Is applied to round-belts which are flexible yet do not strength and can easily be blade-welded. Also often applied to strong buffers and vibration absorbing buffers. | | | |
| Features | | Chemical resistance | |
| feature | DIN | Resistance to | Valutation |
| Relative density gr/cm ³ | 1,26 | Petrol | A |
| Tensile strength MN/m ² | 50 | Benzene | A |
| Elongation at break % | 600 | Mineral oils | A |
| Tensile modulus MN/m ² | 25 | Vegetable oils | A |
| Notched impact strength kJ/m ² | - | Weak alkalis | A |
| Ball indentation MN/m ² | shore A 70 | Strong alkalis | C |
| Application temperature max °C | 80 | Weak acids | B |
| Volume resistivity cm | - | Strong acids | C |
| Dissapation factor tan. 10 ³ Hz | 0,1 | A = good | |
| Dielectric strength MV/m | 20 | B = doubtful | |
| Flammability UL94 > 1,6 mm | HB | C = poor | |
| Coefficient of friction (on steel) | 0,15-0,4 | | |
| All data are indicative | | | |

Technical informations are indicative and can be updated.

Copyright Gandini Fasteners S.r.l. All rights reserved. No part of this web site may be reproduced in any form without express permission.

GANDINI FASTENERS SRL viale Pier Paolo Pasolini, 83 - 20099 Sesto S.Giovanni Milano Italy
Tel. +39 02 241 047 250 Fax +39 02 241 047 74

Production and distribution
of fasteners, fixing elements
and mechanical parts
machining

GANDINI FASTENERS SRL
viale Pier Paolo Pasolini, 83
Sesto San Giovanni Mi - Italy

Sales department
250@gandini.it
tel +39 02 241 047 250

Administration
350@gandini.it
tel +39 02 241 047 350