

TECHNICAL PLASTIC AND METAL PARTS

PCB spacer
100-1

Code	Description	Price euro/1000	Variazione Prezzo %		Confezione	A	B	C	D	E	F	gr
			1	2								
100 1143 000 02	MP 100-1-143	194,00	+ 60%	-	100	14,3	9	6,4	4	4,2		

Colour	Colour number
transparent - natural	000 (XXX XXXX XXX XX)
Colour description transparent - natural Matches Natural matches Milk-like; transparent white colour can differ per kind of material. Featured colours reserved. Due to the screen, differences in colour may occur.	

Material	Material nr
Nylon - 66 PA - 66	02 (XXX XXXX XXX XX)
General informations: A strong, tough and durable material. Suitable for connecting elements and other technical components. Owing to selflubricant properties ideal for slide bearings. Takes in approx 2 % moisture (a little less than nylon-6) and is then at its strongest. Therefore always has to acclimatize for a few days after injection moulding. Operational temperature up to 120°C. Nylon is self extinguishing.	
Features	
feature	DIN
Relative density gr/cm ³	1,14
Tensile strength MN/m ²	60
Elongation at break %	140
Tensile modulus MN/m ²	1500
Notched impact strength kJ/m ²	17
Ball indentation MN/m ²	100
Application temperature max °C	120
Volume resistivity cm	10^15
Dissipation factor tan. 10 ³ Hz	0,15
Dielectric strength MV/m	30
Flammability UL94 > 1,6 mm	V2
Coefficient of friction (on steel)	0,3
All data are indicative	
Chemical resistance	
Resistance to	Valutation
Petrol	A
Benzene	A
Mineral oils	A
Vegetable oils	A
Weak alkalis	A
Strong alkalis	B
Weak acids	B
Strong acids	C
A = good B = doubtful C = poor	

I dati riportati sono indicativi e possono essere in qualsiasi momento variati dai produttori.

Copyright Gandini Fasteners S.r.l. Tutti i diritti sono riservati. Ogni riproduzione, anche parziale, è vietata senza espressa autorizzazione della Gandini Fasteners S.r.l.

GANDINI FASTENERS SRL viale Pier Paolo Pasolini, 83 - 20099 Sesto S. Giovanni Milano - Italy
Tel. +39 02 241 047 250 Fax +39 02 241 047 74 - 250@gandini.it

Production and distribution
of fasteners, fixing elements
and mechanical parts
machining

GANDINI FASTENERS SRL
viale Pier Paolo Pasolini, 83
Sesto San Giovanni Mi - Italy

Sales department
250@gandini.it
tel +39 02 241 047 250

Administration
350@gandini.it
tel +39 02 241 047 350